

Amendments to the Claims:

This listing of claims will replace all prior versions of claims in the application:

1. (Canceled)
2. (Canceled)
3. (Canceled)
4. (Canceled)
5. (Canceled)
6. (Canceled)
7. (Canceled)
8. (Currently amended) The heat sealable film of Claim [[1]] 28, additionally comprising at least one layer comprising a thermoplastic polymer laminated to the at least one layer consisting essentially of the norbornene/ethylene copolymer COC.
9. (Currently amended) The heat sealable film of Claim 8, wherein the at least one thermoplastic polymer layer and the at least one layer consisting essentially of norbornene/ethylene copolymer COC are formed by coextrusion.
10. (Original) The film of Claim 9, wherein the coextrusion is performed using a flat-film die.
11. (Original) The film of Claim 9, wherein the coextrusion is performed by a blown film process.

12. (Currently amended) The film of Claim 8, wherein the at least one thermoplastic polymer layer and the at least one layer consisting essentially of norbornene/ethylene copolymer ~~COE~~ are laminated by adhesive bonding.
13. (Currently amended) The film of Claim 8, wherein the at least one thermoplastic polymer is selected from the group consisting of polyester, polycarbonate, polyolefin, polyacrylate, polyester carbonate, polyamide, polyketone, polyether, polyvinyl, cyclic olefin homopolymer and cyclic olefin copolymer, wherein the at least one thermoplastic layer has a Tg greater than that of the at least one layer consisting essentially of norbornene/ethylene copolymer ~~COE~~.
14. (Original) The film of Claim 13, wherein the thermoplastic is a polyester, polypropylene, polyethylene or nylon.
15. (Original) The film of Claim 14, wherein the thermoplastic is selected from the group consisting of polyethylene terephthalate and polybutylene terephthalate.
16. (Currently amended) The film of Claim 8, wherein the laminate is further heat sealed to another layer via the heat sealable norbornene/ethylene ~~COE~~ polymer layer.
17. (Original) A heat sealed package comprising a film of Claim 8.
18. (Original) The package according to Claim 17, wherein the heat seal is effected at a sealing temperature of from about 50 to about 80°C.
19. (Currently amended) The film according to Claim ~~[[1]]~~ 28, wherein the film exhibits a maximum hot tack strength value at a heat sealing temperature below about 75°C and exhibits a hot tack strength value of at least about 10% of that maximum value at heat sealing temperatures of from about 90°C to about 150°C.

20. (Currently amended) The film according to Claim [[1]] 28, wherein the film exhibits a maximum hot tack strength value at a heat sealing temperature below about 75°C and exhibits a hot tack strength value of at least about 20% of that maximum value at heat sealing temperatures of from about 90°C to about 150°C.
21. (Currently amended) The film according to Claim [[1]] 28, wherein the film exhibits a maximum hot tack strength value at a heat sealing temperature below about 75°C and exhibits a hot tack strength value of at least about 30% of that maximum value at heat sealing temperatures of from about 90°C to about 150°C.
22. (Currently amended) The film according to Claim [[1]] 28, wherein the film exhibits a maximum ultimate strength value at a heat sealing temperature below about 90°C and exhibits an ultimate strength value of at least about 25% of that maximum value at heat sealing temperatures of from about 100°C to about 150°C.
23. (Currently amended) The film according to Claim [[1]] 28, wherein the film exhibits a maximum ultimate strength value at a heat sealing temperature below about 90°C and exhibits an ultimate strength value of at least about 50% of that maximum value at heat sealing temperatures of from about 100°C to about 150°C.
24. (Canceled)
25. (Canceled)
26. (Currently amended) [[A]] The heat sealable film according to claim 28, wherein consisting essentially of a film forming norbornene/ethylene copolymer having a T_g of from about 30°C to about 55°C, a film of the film forming copolymer exhibiting exhibits a hot tack strength of greater than 10N when tested at a heat seal temperature below about 75°C at a seal pressure of 44 psi, a seal time of 1 second, a cooling time of 0.1 second, a film sample width of 1 inch and a film sample thickness of 2 mil, wherein the peel speed is 200 mm/s.

27. (Original) A heat sealable film consisting essentially of a film forming norbornene/-ethylene copolymer having a Tg of from about 30°C to about 55°C, a film of the film forming copolymer exhibiting a hot tack strength of greater than 10N when tested at a heat seal temperature below about 75°C at a seal pressure of 44 psi, a seal time of 1 second, a cooling time of 0.1 second, a film sample width of 1 inch and a film sample thickness of 2 mil, wherein the peel speed is 200 mm/s, wherein further a film of the film forming copolymer exhibits a hot tack strength of greater than about 5N at all heat seal temperatures between about 75°C and 150°C at a seal pressure of 44 psi, a seal time of 1 second, a cooling time of 0.1 second, a film sample width of 1 inch and a film sample thickness of 2 mil, wherein the peel speed is 200 mm/s.
28. (Original) A heat sealable film consisting essentially of a film forming norbornene/-ethylene copolymer having a Tg of from about 30°C to about 55°C, a film of the film forming copolymer exhibiting an ultimate seal strength of greater than 10N when tested at a heat seal temperature below about 90°C at a seal pressure of 44 psi, a seal time of 1 second, a cooling time of 30 seconds, a film sample width of 1 inch and a film sample thickness of 2 mil, wherein the peel speed is 200 mm/s.
29. (Original) A heat sealable film consisting essentially of a film forming norbornene/-ethylene copolymer having a Tg of from about 30°C to about 55°C, a film of the film forming copolymer exhibiting an ultimate seal strength of greater than 10N when tested at a heat seal temperature below about 90°C at a seal pressure of 44 psi, a seal time of 1 second, a cooling time of 30 seconds, a film sample width of 1 inch and a film sample thickness of 2 mil, wherein the peel speed is 200 mm/s, wherein further a film of the film forming copolymer exhibits an ultimate seal strength of greater than about 20N at all heat seal temperatures between about 90°C and 150°C at a seal pressure of 44 psi, a seal time of 1 second, a cooling time of 0.1 second, a film sample width of 1 inch and a film sample thickness of 2 mil, wherein the peel speed is 200 mm/s.
30. (Currently amended) The heat sealable film according to claim 28. ~~A cycloolefin copolymer consisting of norbornene and ethylene, wherein the cycloolefin copolymer has a Tg of from~~

~~about 30 to about 55°C and~~ wherein the norbornene is present in the copolymer in an amount of from about 24 to about 30 mole percent and wherein the ethylene is present in an amount of from about 76 to about 70 mole percent.

31. (New) The film according to claim 13, wherein the at least one thermoplastic polymer is a norbornene/ethylene copolymer having a Tg of from about 30°C to about 55°C.